

BIOCLEAN-D

STERILE LONGER LENGTH

Overboots

S-BDOB-L

About

Offering exceptional comfort and protection, the single-use BioClean-D Sterile longer (height 500mm) Overboots are constructed from anti-static low-linting CleanTough material, and feature a slip-resistant sole and easy tie-fastenings at the top and ankle.

Specifications

MATERIAL:

Anti-static BioClean-D CleanTough white material & polyurethane sole

COLOUR:

White

CONSTRUCTION:

Bound seams with single needle stitching

CLASSIFICATION:

PPE Cat 3 Type PB [6]

CHARACTERISTICS:

Anti-static to EN 1149-5* & low particulating

COMPATIBILITY:

ISO Class 4

STERILIZATION:

Gamma irradiation

TOP & ANKLE TIES

ANTI-STATIC

SLIP-RESISTANT SOLE

SILICONE-FREE

Features

- Longer length - 500mm
- Low-linting
- Tie-fastenings at top & ankle
- Slip-resistant sole

EN 13034:2005 + A1:2009 EN 1149-5: 2008



TYPE PB[6]



Quality Standards

- Manufactured in a facility holding ISO 9001:2015 and (EU)2016/425 Module D certifications
- Conforms to Category 3 - Personal Protective Equipment PPE Regulation (EU)2016/425
- Tested against standard EN ISO 13034:2005+A1:2009 protective clothing against liquid chemicals (Type PB[6])
- Tested against standard EN ISO 14325 protective clothing against chemicals
- Tested against standards: EN 1149-5:2008*, protective clothing - electrostatic properties; EN 530, Abrasion resistance; EN 7854, Flex cracking resistance; EN 6530, Resistance to penetration by liquids; EN 13934-1, Tensile strength; EN 9073-4, Trapezoidal tear resistance; EN 863, Puncture resistance; and EN 13935-2, Seam strength
- Tested against permeation standard ASTM F739-12
- Processed in an NEBB certified ISO Class 4 environment
- Sterilized in accordance with ISO 11137-1:2006

Sterilization

Method: Gamma irradiation
 Minimum Dose: 25kGy
 Sterility Assurance Level: 10^{-6}

Shelf Life & Storage

Three (3) years from date of manufacture. Store in a dry, cool place (<40°C) away from direct sunlight and fluorescent light.

Performance Test Results – BioClean-D CleanTough White Material

TEST	RESULT		PERFORMANCE CLASS (EN 14325)
Abrasion Resistance	10 to 100 cycles		1
Flex Cracking Resistance	2,500 to 5,000 cycles		2
Trapezoidal Tear Resistance	CD 29.3 N		2
Trapezoidal Tear Resistance	MD 55.5 N		3
Tensile Strength	MD 97 N		2
Tensile Strength	CD 48 N		1
Puncture Resistance	8 N		2
Repellence to Liquids	30% H ₂ SO ₄	96.3%	3
	10% NaOH	97.6%	3
	O-Xylene	95.7%	2
	Butan-1-ol	96.6%	3
Penetration by Liquids	30% H ₂ SO ₄	0%	3
	10% NaOH	0%	3
	O-Xylene	0%	3
	Butan-1-ol	0%	3
Seam Strength ¹	70 N		3
Electrostatic Charge Half Decay Time, t_{50} (secs)	0.07		PASS

¹Seam not destroyed

Particle Shedding Test Results

TEST	RESULT	CATEGORY (IEST-RP-CC003.3)
Particle Shedding (Helmke Drum Test)	<260	Category I

BioClean-D™ CleanTough White Material - ASTM F739-12 Test Method Results

Mean Breakthrough Time (MBT), Minutes

Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.1 µg/cm²/min

CISPLATIN	CARMUSTINE	CYCLO- PHOSPHA- MIDE	DOXO- RUBICIN HYDRO- CHLORIDE	5- FLURO- URACIL	METHO- TREXATE	ETOPOSIDE	PACLITAXEL	THIOTEPA
>240	<6	217 (275,162,215)	>240	>240	>240	>240	<10	30 (28,30,33)

Results achieved under controlled laboratory conditions, by accredited external testing laboratory.

TO ORDER

Re-Order	Chest	Height	Size
S-BDOB-L	N/A	N/A	Universal

Packing

One pair per sealed inner PE bag; 15 inner bags per sealed outer PE bag; five outer bags per lined carton (75 pairs)

*NOTE: BioClean CleanTough material is static dissipative and, with a charge half decay time of 0.07 sec, S-BDOB-L are ideal for use in a static-safe environment. However S-BDOB-L should not be relied upon to earth the wearer.

For additional information visit us at www.bioclean.com, or call us at +44 1638 663338

Nitritex Ltd

Minton Enterprise Park,
Oaks Drive
Newmarket, Suffolk, CB8 7YY
United Kingdom
Tel: +44 1638 663338

Ansell US

111 Wood Avenue South
Suite 210
Iselin, NJ 08830
USA
Tel: +1 800 800 0444

Nitritex (M) Sdn Bhd

No.2, Jalan Jurunilai U1/20, Seksyen U1
Hicom Glenmarie Industrial Park
40150 Shah Alam, Selangor
Malaysia
Tel: +603 5569 3857/3859

S-BDOB-L/1906/PDS10

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of disposable garments for a specific application.

**Please see product validation pack or contact Ansell customer service for specific data on use of garments with cytotoxic drugs. Garments used for protection against such drugs must be selected specifically for the type of chemicals used.

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. © 2012 – 2019 Ansell Limited. All Rights Reserved.

